



Specification Sheet

LB200G

Property	Test Method	Typical Value
Grab Tensile	ASTM-D-4632	220 Lbs
Grab Elongation	ASTM-D-4632	15%
Mullen Burst	ASTM-D-3786	440 psi
Puncture	ASTM-D-4833	115 Lbs
Trapezoid Tear	ASTM-D-4533	80 Lbs
AOS	ASTM-D-4751	40 sieve
Permittivity	ASTM-D-4491	0.08 sec ⁻¹
Flow Rate	ASTM-D-4491	6gal/min/ft ²

The above information is to the best of our knowledge accurate, but is not intended to be considered as a guarantee. Any implied warranty for a particular use or purpose is excluded. If the Product does not meet the above properties, and notice is given to Link Bridge, the product will be replaced or refunded. (1/2012).

#301, 10-7, SAMSEONG-DONG,
GANGNAM-GU,
Seoul, Korea
Tel: 82-2-725-2126 Korea
(415) 867-0920 USA West
Fax: 82-2-725-2127 Korea
(415) 366-1662 USA
www.linkbridgeco.com